

PRODUCT SHEET

PIRENEI BLACK S3 WR HRO SRC

 Prod. Ref.
 80350-006

 Safety cat.
 S3 WR HRO SRC

 Range of sizes
 39 - 48 (6 - 13)

 Weight (sz. 8)
 780 g

 Shape
 B

11

Widht

Description: Black water repellent full grain leather ankle boot, **SANY-DRY**[®] lining, antistatic, anti-shock, slipping resistant, non metallic **APT Plate** midsole **Zero Perforation**.

Plus: Full **SOFT-BED** footbed, made of soft and scented polyurethane, antistatic, anatomic, holed, soft and comfortable. The upper layer absorb moisture and keep the foot dry. Cold and heat insulation. Arch support made of polycarbonate and fibreglass conveniently placed between heel and sole, which provides support and protection of the plantar arch, thus preventing harmful bendings. Outsole resistant to +300°C (1 minute contact). Padded collar. **Sealed stitchings.**

Suggested uses: Construction, maintenance, industries.

Care and maintenance: Clean after each use and dry off away from direct heat; treat the leather with a suitable shoe-polish. Avoid contact with aggressive chemicals or extreme temperature. Avoid immersion in sea water, lime water or cement mixed with water.



MATERIALS / ACCESSORIES

SAFETY TECHNICAL SPECIFICATIONS

			Clause EN ISO 20345:2011	Description	Unit	Cofra result	requirement
Whole footwear	Water resistance		5.15.1	Water resistance (area of water penetration after 1000 paces in a surface flooded with water)	cm ²	≤ 3	≤ 3
Complete shoe	Toe cap: non	metallic TOP RETURN toe cap, impact resistant until 200 J	5.3.2.3	Shock resistance (clearance after shock)	mm	15	≥ 14
	and	d compression resistant until 1500 kg	5.3.2.4	Compression resistance (clearance after compression)	mm	14,5	≥ 14
	Anti perforati	on midsole: in multi-layers highly tensile fabric, penetration resistant, Zero Perforation	6.2.1	Penetration resistance	N	To 1100 N	≥ 1100
						No Perforation	
	Antistatic shoe: the bottom is fit for the dissipation of electrostatic charges		6.2.2.2	Electric resistance			
				- wet	$M\Omega$	45	≥ 0.1
				- dry	$M\Omega$	880	≤ 1000
	Energy absorption system		6.2.4	Shock absorption	J	32	≥ 20
Upper	Black water repellent full grain leather		5.4.6	Water vapour permeability	mg/cmq h	> 0,8	≥ 0,8
	thickness 1,6/	1,8 mm		Permeability coefficient	mg/cmq	> 15	> 15
			6.3.1	Water absorption		20%	≤ 30%
				Water penetration		0,1 g	≤ 0,2 g
Vamp	Textile, breathable, abrasion resistant, colour black		5.5.3	Water vapour permeability	mg/cmq h	> 9,4	≥ 2
lining	thickness 1,2 mm			Permeability coefficient	mg/cmq	> 75,7	≥ 20
Quarter	SANY-DRY®, antibacterial, breathable, abrasion resistant, colour black		5.5.3	Water vapour permeability	mg/cmq h	> 6,7	≥ 2
lining	thickness 1,2 mm			Permeability coefficient	mg/cmq	> 54,1	≥ 20
Sole	Polyurethane/Nitrile rubber, antistatic, resistant to high temperatures, directly injected in the upper:		5.8.3	Abrasion resistance (lost volume)	mm^3	105	≤ 150
			5.8.4	Flexing resistance (cut increase)	mm	1,5	≤ 4
	Outsole:	black nitrile rubber, slipping resistant, abrasion resistant, hydrocarbons	5.8.6	Interlayer bond strength	N/m	> 5	≥ 4
		resistant and heat resistant.	6.4.4	Hot resistance (300 °C)		any melting	any melting
	Midsole:	black polyurethane, low density, comfortable and anti-shock.	6.4.2	Hydrocarbons resistance (ΔV = volume increase)	%	+ 1,6	≤ 12
	Adherence coefficient of the sole		5.3.5	SRA : ceramic + detergent solution - flat		0,54	≥ 0,32
				SRA : ceramic + detergent solution – heel (contact angle 7°)		0,50	≥ 0,28

SRB : steel + glycerol – flat $0,23 \ge 0,18$ SRB : steel + glycerol – heel (contact angle 7°) $0,18 \ge 0,13$